

## 测试报告

报告编号: **ASH18-010356-01**

签发日期: **2018-03-26**

客户名称: 宁波美材美质科技发展有限公司  
客户地址: 宁波市余姚文山创意广场 20 栋 312  
样品名称: PPR 塑料片  
样品批号: PPR001-16  
生产日期: /  
生产商: /

以上样品及信息由客户提供及确认, **SGS 不承担证实客户提供信息的准确性、适当性和(或)完整性责任。**

SGS 样品编号: ASH18-010356.001  
SGS 相关号: Q-NBAFL201800097433  
样品接收日期: 2018-03-16  
样品测试日期: 2018-03-16 ~ 2018-03-26

**测试要求:**  
根据申请者的要求:  
抗菌效果实验

**测试方法:**  
请参见下页

**测试结果:**  
请参见下页

除非另有说明, 本检验结果仅对测试样负责, 仅供客户内部使用, 不对社会具有证明作用。未经检验机构书面同意, 委托人不得擅自使用检验结果进行不当宣传。



通标标准技术服务(上海)有限公司  
第 1 页 共 2 页



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.  
Testing Center Agri. & Food Prod. Laboratory

3<sup>rd</sup> Building, No. 889, Yishan Road, Shanghai, China 200233

t 400 - 691 - 0488

f (86-21) 6140 2547

[www.sgsgroup.com.cn](http://www.sgsgroup.com.cn)

中国 · 上海 · 宜山路889号3号楼

邮编: 200233

t 400 - 691 - 0488

f (86-21) 6140 2547

e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

## 测试报告

报告编号: **ASH18-010356-01**

签发日期: **2018-03-26**

### 测试方法:

ISO 22196:2011 塑料和其他非多孔表面抗菌活度的测量

### 实验菌种:


金黄色葡萄球菌 ATCC 6538P, 大肠杆菌 ATCC 8739

### 测试结果:

实验菌种	接种菌液浓度 (cfu/mL)	接种菌液量 (mL)	在不同接触时间洗脱后获得的细菌数 (cfu/cm <sup>2</sup> ) 对数值			抗菌活性值
			/	"0 小时"	"24 小时"	
大肠杆菌 ATCC 8739	1.6x10 <sup>6</sup>	0.2	样品	/	1.48	4.2
			对照样	4.23	5.71	
金黄色葡萄球菌 ATCC 6538P	1.8x10 <sup>6</sup>	0.2	样品	/	-0.21	6.0
			对照样	4.27	5.79	

注: 对照样为无抗菌性能塑料膜, 由 SGS 实验室提供.

样品描述: 片材



\*\*\* 结束 \*\*\*

通标标准技术服务(上海)有限公司  
第 2 页 共 2 页

